












Highway Design and Construction (Asphalt Lab)

S. No.	Name of instrument	Description	photo
1.	Sieves	<p>Sieves are used for sieve analysis test of gradation gravel in asphalt concrete mixture.</p> <p>Sieves are selected to furnish information required by .specification</p>	
2.	Ductility Machine	<p>Ductility machine is used to determine the ductility of formed asphalt/cement or semi-solid bitumen by measuring the distance of elongation before reaching the breaking point of a briquet sample,</p>	

3	Marshall Compaction Hammer Machine	The Marshall Compaction Hammer is used to compact the Asphalt specimen	
4	Extraction of bituminous machine	Extraction of bituminous machine is used to separate and wash out bituminous from the asphalt sample by using benzene fuel.	

5	Penetration test machine	<p>The penetration test is used to measure consistency of bituminous materials expressed as the distance in tenths of millimeter that a standard needle vertically penetrates a sample of the materials under known conditions of loading, loading time and temperature</p>	
6	Bending beam Rheometer	<p>ATS,s Bending Beam Rheometer (BBR) is designed to provide a state –of-the art means for testing the flexural creep stiffness properties of Asphalt binders in temperature range from -40 °C to 25 °C.(AASHTO Designation T313-02 and ASTM D 6648-01</p>	
7	Centerlaken technology machine	<p>The Centerlaken technology machine is used for high technology test for asphalt mixture</p>	

8	Dynamic Shear Rheometer (DSR) Machine	The DSR is used to measure the strength of bituminous	
9	ATS Applied Test Machine	The ATS Applied Test Machine is used to test the Asphalt according to applied high load and running time	
10	Tensile test machine	The Tensile test machine is used to test the tension of Asphalt	